

# パロニア®

品名	寸法			梱包 (枚)	色
	厚さ(mm)	幅(mm)	長さ(mm)		
パロニア®	3.0	1,300	2,020	5	シロ チャ
	4.0				
	5.0				
	8.0	1,120	2,220	3	チャ
	2.0	1,300	2,020	10	アオ
			1,620		
	3.0	1,300	2,220	5	
			2,020		
			1,820		
			1,620		
	3.0	1,120	2,220	5	
			2,020		
			1,820		
			1,620		
	4.0	1,300	2,220	5	
			2,020		
			1,820		
			1,620		
	5.0	1,300	2,220	4	
			2,020		
1,820					
1,620					
5.0	1,120	2,220	5		
		2,020			
		1,820			
		1,620			
6.0	1,300	2,020	4		
8.0	1,120	2,220	3		
10.0	1,120	2,220	2		

※シロ全厚み・アオ10mm厚:コロナ処理有 その他:コロナ処理無  
 ※特注品についてはご相談に応じます。厚み範囲:2~12mm

品名	項目	単位	試験方法	方向	製品厚み(mm)						
					2.0	3.0	4.0	5.0	6.0	8.0	10.0
パロニア®	引張降伏点応力	MPa	JIS K-7161	MD	7.9	6.9	6.3	—	—	—	—
				TD	7.0	6.7	6.6	—	—	—	—
	引張破断伸度	%	JIS K-7161	MD	85	60	45	—	—	—	—
				TD	45	55	55	—	—	—	—
	曲げ強度	MPa	JIS K-7171	MD	6.9	7.3	7.6	7.5	7.5	9.1	8.8
				TD	4.4	4.9	5.7	6.5	7.1	9.4	10.2
	曲げ弾性率	MPa	JIS K-7171	MD	440	360	330	300	280	340	300
				TD	280	240	240	240	240	310	300